



ATHLETIC & RECREATIONAL SURFACES 02790

Pro-Techs Surfacing LLC v08.2022

1. Product Name

Perma-Play 2-Layer Poured-In-Place Playground Surfacing w/ Aliphatic Urethane

2. Manufacturer

Pro-Techs Surfacing LLC
 P.O. Box 301
 Sharon Center, OH, OH 44274
 (330)-576-6058
info@pro-techssurfacing.com
<http://www.pro-techssurfacing.com>

3. Product Description

BASIC USE

Perma-Play 2-Layer Poured-In-Place Playground Surfacing is designed for playgrounds and water play areas.

COMPOSITION & MATERIALS

Perma-Play 2-Layer Poured-In-Place Playground Surfacing is a 2-layer system. The Buffering material consists of 100% post-consumer recycled, 3/8" shredded, SBR (styrene butadiene rubber) and high-grade aromatic polyurethane. The top surface consists of EPDM (Ethylene Propylene Diene Monomer) rubber, with the black EPDM being recycled post-industrial material, ranging in size from 1 – 3 mm, and high-grade aromatic or aliphatic polyurethane.

PRODCUT DEMINSIONS:

The height of the playground equipment determines the required Buffering thickness. Buffering thicknesses may vary throughout a playground site. Buffering thicknesses are determined by the "Critical Fall Height" requirements through ASTM testing. All ASTM test results are available upon request.

Thicknesses Available

2.00" – up to 4ft. CFH
 2.75" – up to 6ft. CFH
 3.00" – up to 7ft. CFH
 3.50" – up to 8ft. CFH
 4.00" – up to 9ft. CFH
 4.50" – up to 10ft. CFH
 5.00" – up to 12ft. CFH

TOP SURFACE THICKNESS:

0.5" thickness nominally

Colors – (* = Aliphatic Binder is Recommended)

Standard Colors		Premium Colors	
200 Black	210 Purple*	211 White*	251 Orange*
202 Red	231 Bright Green*	234 Purple*	259 Tan*
203 Blue*	232 Terracotta Red	239 Dark Green	261 Blue Grey*
204 Beige*	233 Light Green*	242 Yellow*	262 Eggshell*
205 Green	235 Brown	243 Pearl*	263 Capri Blue
206 Brown	236 Light Grey*	244 Teal*	264 Signal Green
207 Dark Grey*	238 Blue*	247 Dark Blue*	265 Charcoal
208 Yellow*	240 Light Beige*	249 Light Blue*	
209 Orange*	248 Gold*		



ATHLETIC & RECREATIONAL SURFACES 02790

Pro-Techs Surfacing LLC v08.2022

LIMITATIONS

As a precautionary maintenance measure, a list of chemicals known to damage Perma-Play 2-Layer Poured-In-Place Playground Surfacing and similar rubber safety surfaces is available upon request. In water play areas, pool surrounds and similar applications. Pool chemicals may affect coloration of the rubber safety surface over time. This condition, should it occur, is not considered to be a product failure. A “YELLOWISH” shading of the rubber top surface will be noticeable in some colors when using standard aromatic polyurethane binder. This slight yellowing is more pronounced in certain colors and is a common affect in the pour in place rubber safety surface industry. An aliphatic binder, which greatly minimizes the yellowish shading, is available at a higher cost. Both binding materials can be used on a project to maximize aesthetics with lighter colors that are affected by the yellowing and minimize cost. Consult Pro-Techs Surfacing LLC for more information.

4. Technical Data

APPLICABLE STANDARDS

ASTM International

- ASTM D412 Standard Test Methods for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers-Tension
- ASTM D624 Standard Test Methods for Tear Strength of Conventional Vulcanized Rubber and Thermoplastic Elastomers
- ASTM C1028 Standard Test Method for Determining the Static Coefficient of Friction of Ceramic Tile and Other Like Surfaces by the Horizontal Dynamometer Pull Meter Method
- ASTM D2859 Standard Test Method for Flammability of Finished Textile Floor Covering Materials
- ASTM E303 Standard Test Method for Measuring Surface Frictional Properties Using the British Pendulum Tester
- ASTM F1292 Standard Specification for Impact Attenuation of Surface Systems Under and Around Playground Equipment
- ASTM F1951 Standard Specification for Determination of Accessibility of Surface Systems Under and Around Playground Equipment

ENVIRONMENTAL CONSIDERATIONS

This system makes extensive use of recycled tire rubber as a major component.

PHYSICAL/CHEMICAL PROPERTIES

- Shock Attenuation (ASTM F1292)
 - Gmax - Less than 200
 - Head Injury Criteria – 1000 or less
- Accessibility (ASTM 1951)
 - Straight Baseline Propulsion - 12.15 lbs Work/ft-Force
 - Turning Baseline Propulsion - 7.30 lbs Work/ft-Force
- Tensile Strength (ASTM D412) – 163.18PSI
- Tear Resistance (ASTM D624) – 60.96PSI
- Dry Static Coefficient of Friction (ASTM C1028) - 0.77
- Wet Static Coefficient of Friction (ASTM C1028) - .56
- Wet Skid Resistance (ASTM E303) - Initial Dry 88.5BPN, 90 Degree Dry 96.8BPN
- Flammability (ASTM D2859) – Pass
- Water Permeability (ASTM F1551-03) gal/min/yd² = 363.5

Required mix proportions by weight:

Basement – 14% - 16% polyurethane, 100# rubber

Top course – 22% - 26% polyurethane, 100# - 110# rubber



ATHLETIC & RECREATIONAL SURFACES 02790

Pro-Techs Surfacing LLC v08.2022

5. Installation

PREPARATORY WORK

EPDM Rubber materials should be protected from exposure to harmful environmental conditions (moisture) and at a minimum temperature of 50 degrees F and a maximum temperature of 90 degrees F. Install surfacing system when minimum ambient temperature is 50 degrees F and maximum ambient temperature is 90 degrees F. Pro-Techs Surfacing may at its discretion, choose to commence a cold weather installation on projects less than 1000sf in size. This decision is solely at the discretion of Pro-Techs Surfacing and will not affect the standard product warranty. Buffing may be installed in a light rain. Do not install Topcoat in any type of moisture or precipitation.

SUBSTRATE PREPARATION

1. Compacted Stone Base

Substrate must be in accordance with surfacing manufacturers Compacted Stone Base Installation Instructions before Perma-Play 2-Layer Poured-In-Place Playground Surfacing can be applied.

2. Asphalt Substrate

New asphalt substrates must be allowed to cure for a minimum of 30 days before Perma-Play 2-Layer Poured-In-Place Playground Surfacing can be applied.

3. Concrete Substrate

New concrete substrates must cure for a minimum of 10 days before Perma-Play 2-Layer Poured-In-Place Playground Surfacing can be applied.

NOTE: Proper drainage is crucial to the longevity of the Perma-Play 2-Layer Poured-In-Place Playground Surfacing. Inadequate drainage will cause premature breakdown of the product in affected areas; and void the warranty.

BASIC METHODS

Installation

Perma-Play 2-Layer Poured-In-Place Playground Surfacing cannot proceed until all applicable site work, including substrate preparation, fencing, playground equipment installation and other relevant work, has been completed and approved by a Pro-Techs Surfacing LLC representative.

Buffing Primer

Using a bristle brush, apply ample urethane primer to all curbing and or vertical substrates, which the rubber surfacing system will contact.

Buffing Installation

Using screed sticks and gauge poles, install the Buffing rubber materials to 1/8" – 1/4" higher than required thickness. Using pool trowels, pull the Buffing material together using consistent pressure throughout. Repeat the process until all areas, including use zones, comply with the architectural plans and specification requirements. Allow Buffing to cure for sufficient time (24 hours) so that indentations are not left in the Buffing material. Installation contractor must verify that the Buffing has cured sufficiently before applying the finished topcoat

Topcoat Primer

Using a bristle brush apply urethane binder to the existing 1/2" of curbing and any other vertical structures within the installation areas, and also to the Buffing material at a minimum of 2" around the perimeter of the topcoat area.

Topcoat Installation

Screed the EPDM topcoat rubber granules to a nominal 5/8" thickness to allow for compaction. Using a pool trowel, pull together material using consistent pressure throughout to produce the end result of 1/2" thickness. Any area in excess of 2500 sf may be seamed as deemed necessary by Pro-Techs Surfacing, LLC. Any area less than 2500 sf will be completed seamlessly as conditions allow.



ATHLETIC & RECREATIONAL SURFACES 02790

Pro –Techs Surfacing LLC v08.2022

* **NOTE** – Allow topcoat to cure for 48 hours to 72 hours contingent on the humidity and temperature. Protect newly installed topcoat from foot traffic or equipment usage until the Perma-Play 2-Layer Poured-In-Place Playground Surfacing has fully cured. Complete installation recommendations are available from a Pro-Techs Surfacing LLC representative.

6. Warranty

Standard warranty period for Perma-Play 2-Layer Poured-In-Place Playground Surfacing is for 5 years from completion of installation. Contact Pro-Techs Surfacing, LLC for 7 year & 10 year warranty options.

7. Maintenance/Cleaning – Outdoor & Indoor Applications

Outdoor Applications -

Using a standard leaf blower or broom, remove any light weight debris such as leaves, trash, etc. Using a watering hose or a pressure washer, not exceeding 1000 PSI, rinse off all excess debris from the surface. While surface is wet, apply a mild cleaning detergent and agitate lightly with a soft bristle brush. Repeat as necessary. Once clean, final rinse with low-pressure water from a hose to remove any excess- cleaning agents.

Indoor Applications –

Using a standard vacuum cleaner/shop vac, or broom, remove any light weight unwanted debris. Apply a mild cleaning detergent and agitate lightly with a soft bristle brush or mop. Repeat as necessary. Once clean, final mop with clean hot water to remove any excess detergent. Be sure to not saturate the mop head. Mop head should be damp at most.

8. Technical Services

Pro-Techs Surfacing LLC works closely with the contractor to ensure the site is prepared and the installation is on schedule. For technical assistance, contact Pro-Techs Surfacing LLC.

9. Quality Assurance

Qualifications – Utilize an installer certified and trained by the manufacturer of playground surfacing system, having experience with other projects of the scope and scale of the work described in this section.

Certifications – Certification by manufacturer that installer is an approved applicator of Perma-Play 2-Layer Poured-In-Place Playground Surfacing.

International Play Equipment Manufacturers Association (IPEMA) Certified

Field Supervisor to be present onsite who is employed by the manufacturer as a W2 payroll employee, must be CPSI Certified, Triax Certified, and a OSHA30 card holder to ensure quality control for projects that exceed a contract value greater than \$100,000.00.